

Porcelain

Durastone

Specifications:



Environmentally
Friendly



Slip
resistant



Chemical
resistant




Stain
resistant




Abrasion
resistance



Thermal
resistance



Long
lasting




10
year guarantee

Dimension -	900 x 300 mm, 600 x 600 mm, 600 x 300 mm, 300 x 300mm	
Water absorption -	0.07% - 0.08%, all surfaces	
Determination of dimensions -	- Length max 0.1% - Warpage max 0.2% - Straightness of sides max 0.0% - Edge curvature max 0.1% - Thickness max 3.0%, - Rectangularity max 0.3% - Centre curvature max 0.2% Applies to all surfaces (over 10 x nom 600 x 300 mm tiles)	
Breaking strength -	2515N / 573 lbf, all surfaces except stream 2057N / 466 lbf, stream	
Abrasion strength -	140mm ³ , all surfaces	
Thermal shock resistance -	No damage, all surfaces	
Slip resistance I (Oil wet ramp test) -	15.7° - R10, Relief 13.5° - R10, Matt 19.1° - R11, Rockface 6.1° - R9, Honed 23.7° - R11, Brushed 27.1° - R12, Stream	
Slip resistance II (Wet pendulum test) -	- Wet: 36 - P3, Relief - Wet: 42 - P3, Matt - Wet: 41 - P3, Rockface - Wet: 25 - P2, Honed - Wet: 47 - P4, Brushed - Wet: 47 - P4, Stream	
Slip resistance III (Dynamic coefficient of friction) -	- Wet: 0.61, Relief - Wet: 0.61, Matt - Wet: 0.49, Rockface - Wet: 0.45, Honed - Wet: 0.67, Brushed - Wet: 0.65, Stream	
Chemical resistance -	Passed - All test chemicals - Relief, Matt, Brushed, Rockface and Stream - Household and pool chemicals - Super Polished and Honed	
Stain resistance -	Passed, all surfaces	
Frost resistance -	No damage, all surfaces	
Shade variation -	Within V2, all surfaces	
Warranty (year) -	10 Years	

Please contact us on 03 366 9839 to request any samples or other product details.

international
flooring solutions

p 03 366 9839 e office@robertmalcolm.co.nz
59 Halwyn Drive, PO Box 914, Christchurch 8140, New Zealand
robertmalcolm.co.nz


robert malcolm